

Savan Group

PO Box 2061 Steyning Sussex BN5 0AQ UK

Tel: +44 1903 815702

Fax: +44 1903 815759



TYPICAL ANALYSIS / SPECIFICATION

PRODUCT : LANOLIN ANHYDROUS
SHELF LIFE : THREE YEARS SUBJECT TO CORRECT STORAGE

Test	Specification	Result
Appearance	Slightly yellow	Conforms
Melting point	38-44°C	39°C
Acid value	<1.12	0.85
Saponification value	92-103	97
Iodine value	18-36	29
Residue on ignition	<0.15%	0.08%
pH value	Neutral	Neutral
Chloride value	<0.08	<0.3
CAS No.	8006-54-0	8006-54-0
Loss drying	<0.5%	0.15%
Water absorbtion	>200	258
Peroxide value	<20	18
Alpha	<10	9-

Lanolin is derived from 100% Australian wool grease

Conclusion – It conforms to USP24